



Test Report

No. AJD2709110

Date: SEP.21,2007

Page 1 of 3

READ AND COMPANY

727 VENICE BLVD. LOS ANGELES, CA 90015, USA

The following sample(s) was / were submitted and identified on behalf of the client as:

Product Description: DIAMOND PREMIUM BANNER FR

Style/Item NO.: 1000D×1000D 18×18 520GSM

We have tested the submitted sample(s) as requested and the following results were obtained:

Test Required:

Perform the following test items: Test Method 1 of NFPA 701: Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2004 Edition.

Test Results: -- See attached sheet --


Conclusion: The Test Result Met the Requirements of Method 1 in NFPA 701 2004 Edition.

Test Duration:

Sample Receiving Date : SEP.17, 2007

Test Performing Date : SEP.17, 2007 TO SEP.20, 2007

Signed for and on behalf of
SGS-CSTC Co., Ltd.


Winsen Wang
Supervisor

This Test Report is prepared by the Company subject to its General Conditions of Service printed separately or attached. Said Conditions are also available on the Company's website at www.sgs.com. Attention is drawn to the terms, limits of liability, indemnification and jurisdictional provisions set forth therein. The results set forth in this Test Report refer only to the sample(s) tested and are not intended to represent any other sample(s) and retained for testing. This Test Report shall not be reproduced or used in full, without written approval of the Company.



AJDC 108537

Address: 727 Venice Blvd., Los Angeles, CA 90015, USA Tel: +1 213 749 9762 Fax: +1 213 749 9763 Email: read@sgs.com
Address: 21300 Central Expressway, Fremont, CA 94538, USA Tel: +1 510 470 8800 Fax: +1 510 470 8801 Email: read@sgs.com



Test Report

No. AJD2709110

Date: SEP.21.2007

Page 2 of 3

I. Test sample and condition

Sample Description	DIAMOND PREMIUM BANNER FR
Conditioning	30 minutes T: 105°C±3°C

II. Test Conducted: NFPA 701:2004 Edition Standard Methods of Fire Tests For Flame Propagation of Textiles and Films : Test Method 1

① Test Results:


Specimen No:	Mass of specimen Before test	Mass of specimen After test	Percent of sample's mass loss	After flame time	Burning time(falls to the bottom)	Deviation from Average	Conclusion
1	31.01g	30.98g	0.1%	0.0	0.0(No Drip)	0.3%	PASS
2	31.43g	31.28g	0.5%	0.0	0.0(No Drip)	0.1%	PASS
3	31.32g	31.23g	0.3%	0.0	0.0(No Drip)	0.1%	PASS
4	31.39g	31.24g	0.5%	0.0	0.0(No Drip)	0.1%	PASS
5	31.10g	30.95g	0.5%	0.0	0.0(No Drip)	0.1%	PASS
6	31.30g	31.25g	0.2%	0.0	0.0(No Drip)	0.2%	PASS
7	31.15g	31.02g	0.4%	0.0	0.0(No Drip)	0.0%	PASS
8	31.39g	31.26g	0.4%	0.0	0.0(No Drip)	0.0%	PASS
9	31.51g	31.45g	0.2%	0.0	0.0(No Drip)	0.2%	PASS
10	31.28g	31.11g	0.5%	0.0	0.0(No Drip)	0.1%	PASS
AVE	31.29g	31.18g	0.4%	0.0	0.0(No Drip)	0.1%	PASS

② Criteria for test method 1:

1. Fragments or residues of specimens that fall to the floor of the test chamber shall not continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimens.
2. The average weight loss of the 10 specimen in a sample shall be 40 percent or less.
3. No individual specimen's percent mass loss shall deviate more than 3 standard deviations from the mean for the 10 specimens.
4. When a retest is required, no individual specimen's percent mass loss in the second set of specimens shall deviate from the mean value by more than 3 standard deviations calculated for the second set.
5. When a sample does not demonstrate passing performance in accordance with all of the conditions indicated above, the material shall be recorded as having failed Test Method 1.

To be continued..

This Test Report is issued by the Company subject to its General Conditions of Service printed on each of its reports and available on its website or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and other general terms and conditions therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and do not constitute a commitment for any day. This Test Report shall not be reproduced except in full, without written approval of the Company.



SGS Testing Services (China) Co., Ltd. (SGS 检测服务(中国)有限公司)
 213000 Shanghai, China (213000 上海, 中国)
 Tel: +86 (21) 6389 9199 Fax: +86 (21) 6389 9198
 E-mail: china@sgs.com Website: www.sgs.com

SGS Testing Services (China) Co., Ltd.
 213000 Shanghai, China
 Tel: +86 (21) 6389 9199 Fax: +86 (21) 6389 9198
 E-mail: china@sgs.com Website: www.sgs.com



Test Report

No. AJD2709110

Date: SEP.21.2007


Page 3 of 3

③ Observations

Item	Record
Sample color	WHITE
Density	521.5 g/m ³
Vigorousness of burning	NO
Material molten dripping	NO
Odor smoke	YES


Remark: As per client requirement, the test was performed in accordance with the Test Method 1 of NFPA 701: 2004 Edition

Photo Appendix:



End of Report

This Test Report is issued by the Company subject to its General Conditions of Service printed hereof or attached hereto. It is not to be used as a warranty or upon reliance of the accessible at www.sgs.com. Attention is drawn to the limitations of liability, implied and otherwise, set forth therein. The results shown in this Test Report refer only to the sample(s) tested, unless otherwise stated and do not constitute a guarantee for 90 days. This Test Report shall not be reproduced except in full, without written approval of the Company.



SGS (Singapore) Pte. Ltd. 100 Robinson Road, Singapore 068976
SGS (China) Pte. Ltd. 100 Robinson Road, Singapore 068976
SGS (India) Pte. Ltd. 100 Robinson Road, Singapore 068976
SGS (Malaysia) Pte. Ltd. 100 Robinson Road, Singapore 068976
SGS (Thailand) Pte. Ltd. 100 Robinson Road, Singapore 068976
SGS (Vietnam) Pte. Ltd. 100 Robinson Road, Singapore 068976